

SPA-133  
热固型可剥保护胶

## 产品说明书

**产品介绍** 本产品采用性能优异的树脂为原材料，经过多道工序加工制成；产品无溶剂挥发，固化成膜性能优异，具有良好的绝缘、防潮和保护效果，尤其适用于触摸屏生产过程中的各类保护，具有高洁净度。

**特点** 具有适宜的粘性，易于丝印，固化后膜层均匀，无结点，无杂质；  
产品具有优异的防划伤、防磨损及除尘效果；  
固化后具有非常强韧的拉伸性，良好的弹性，易于剥离操作；  
剥离后无白雾，无残胶，具有高洁净度

**特性**

固含量	100%
颜色	蓝色（黑/白/透明可定制）
固化温度	130℃~150℃
固化时间	10~20min
固化后膜层拉伸强度	>6.0MPa
固化后膜层断裂伸长率	>200%
适用网版	60~300目钢网、丝网
刮刀	低硬度刮刀利于获得更好膜层效果
刮印压力	2.0~3.5Kg/cm <sup>2</sup>

**注意事项**

1. 使用前搅拌10~15min，静置20分钟以上，利于减少气泡、毛边、溢边等现象。
2. 产品黏度可能随温度等环境因素而改变。同时，本品添加的特殊触变成分，可使胶体通过机械搅拌，达到降低黏度的效果，使用时可根据丝印工艺对胶体进行适当搅拌以调节黏度。
3. 未使用完的产品请密封处理，并放置于冷暗指定地点存放。
4. 油墨需经过确定符合质量要求后再进行大批量印刷。

**Notes:** The information contained in this data sheet is intended to assist you in designing with Incheng products. The technical information and datas should be considered representative or typical only. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for particular purpose or that the results shown on this data sheet will be achieved by user for a particular purpose. The user should determine the suitability of Incheng adhesive tape for each application.

深圳仁盛化成材料技术有限公司

Incheng Chemical Co., Ltd



Tel: (+86)755-86962203

Fax: (+86)20-38892205

www.incheng.net